

Direction for use: Koinonina Stone Glue

Down load and read full safety data sheet online.

Work space needs to be well ventilated area. Do NOT apply in rainy or bad poor weather. Short-term exposure limit (15-minute): WEL 250 ppm 1080 mg/m³ WEL = Workplace Exposure Limit. Long-term exposure limit (8-hour TWA): WEL 100 ppm 430 mg/m³

Precautions for safe handling Read and follow manufacturer's recommendations. Remove contamination with soap and water or recognised skin cleansing agent. Do not use organic solvents. Good personal hygiene procedures should be implemented. Wash hands and any other contaminated areas of the body with soap and water before leaving the work site.

Do not eat, drink or smoke when using the product.

The surface to be treated must be dry and clean.
Wear hand protection - Plastic gloves or surgical gloves.
Wear face mask for vapours and fumes.

We recommend a trial run a test with a small amount before you put on the planned project.

Place the appropriate amount, dollop of glue on to a clean plastic tray (old ice cream top butter lid or a old food tray

we recommend a disposable container.

Mix up appropriate amount needed for your job well with a plastic spreader or plastic spoon before you add any hardener product or setting agent.

Colour Pigments:Just add a tinny drop of any colour pigment to our koinonia stone glue and mix it in well with a spatula. Create all the colours of the rainbow to match in the worktop colours and fill holes in the stone.

Mix 1-3 parts Hardener to 100 Parts Koinonia Stone Resin Glue

or mix 1-3% Parts of Hardener per dollop of glue according to working temperature and hardening time you want.

1%= Avg setting time 5-8 minutes.

3%=Avg setting time 2-3minutes.

Amounts = No more than 250g of product or 1/4 of the tin so you do not inhale large amounts poisonous fumes vapours!

Danger Hazard statements

H226 Flammable liquid and vapour.

H315 Causes skin irritation.

H319 Causes serious eye irritation.

H332 Harmful if inhaled.

SETTING -ASAP quickly before it sets in you tub get it spread onto the joining area or fill them holes.

Setting times can vary normal 2-5 minutes. Too much hardener can make it week and brittle.

Please allow a further 20 minutes before moving the stone / work piece. full cure over 1 -2 hours for work to fully.

The information provided has been compiled on the basis of our current knowledge and is believed to be in accordance with the requirements of the Dangerous Substances Directive, Dangerous Preparations Directive and Safety Data Sheets Directive. The information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any particular conditions or process. The conditions and extent of storage and use of material are outside of our control and within the control of the possessor or user. Consequently it is the responsibility of the possessor or user to satisfy themselves as to the completeness of such information and the suitability of the material for their own particular circumstances, conditions or use.